

| C.ART | DESIGNATION | Humidité | hors poussière | | | Surcouchage | | | | | | Ponçable | | | Réticulation | | |
|----------|---------------------------|----------|----------------|------|------|-------------|------|------|------|------|------|----------|------|------|--------------|------|------|
| | | | 10°C | 20°C | 35°C | 10°C | | 20°C | | 35°C | | 10°C | 20°C | 35°C | 10°C | 20°C | 35°C |
| | | | | | | Mini | maxi | Mini | maxi | Mini | maxi | | | | | | |
| 640..... | Laque Altura 92 | 60% | 12h | 6h | 3h | 24h | 4j | 18h | 3j | 16h | 2j | | | | | | |
| 668..... | Laque PU FUTURA | 60% | 50' | 40' | 20' | 24h | 48h | 8h | 48h | 2h | 24h | 36h | 24h | 12h | 7j | 7j | 7j |
| 685..... | Laque PU CHALLENGER | 60% | 5h | 3h | 30' | 12h | 3j | 8h | 3j | 4h | 1j | 48h | 24h | 18h | 7j | 7j | 7j |
| 635..... | Laque BISE | 60% | 2h | 1h | 30' | 8h | 48h | 8h | 48h | 4h | 24h | 24h | 24h | 18h | 7j | 7j | 7j |
| 644415 | Laque epoxy a l'eau STORM | 60% | 7h | 6h | 3h | 7h | 48h | 6h | 48h | 4h | 48h | 48h | 24h | 7j | 7j | 7j | 7j |

| C.ART | DESIGNATION | Humidité | hors poussière | | | Surcouchage | | | | | | Ponçable | | | | | |
|--------|-------------------------------|----------|----------------|------|------|-------------|------|------|------|------|------|----------|------|------|--|--|--|
| | | | 5°C | 20°C | 35°C | 5°C | | 20°C | | 35°C | | 5°C | 20°C | 35°C | | | |
| | | | | | | Mini | maxi | Mini | maxi | Mini | maxi | | | | | | |
| | | | | | | | | | | | | | | | | | |
| 643000 | Vernis Altura UV brillant | 60% | 5h | 3h | 1h | 24h | 5j | 18h | 4j | 16h | 3j | 36h | 24h | 18h | | | |
| 643000 | Vernis Altura UV satiné | 60% | 3h | 2h | 1h | 24h | 5j | 18h | 4j | 16h | 1j | 36h | 24h | 18h | | | |
| 685000 | Vernis Challenger UV brillant | 60% | 5h | 2h | 30' | 12h | 3j | 8h | 3j | 6h | 36h | 48h | 24h | 18h | | | |
| 647000 | BIOWOOD incolore | 60% | 1h | 30' | 20' | 24h | | 12h | | 8h | | | | | | | |

